

Page 3, Lines <sup>9</sup>~~11~~-16:JB.  
8/14/07

This Invention comprises ~~[[of]]~~ the process of adding binder pitch to the mixture of 15 ~~[[--]]~~ to 100 wt % of the calcined cokes and 0 ~~[[--]]~~ to 85 wt % of carbonaceous material, and then kneading, forming, baking and graphitizing.

The characteristics of this Invention ~~[[is]]~~ are to use calcined cokes obtained by coking and calcining after ~~[[the]]~~ mixing crude heavy oil containing 10 ~~[[--]]~~ to 25 wt % of quinoline insoluble with 3 ~~[[--]]~~ to 20 wt % of carbon black.